

aterial Data Sheet PTFE coated glass fabric, Type A7068

| Material: | PTFE coated glass fabric |
|--------------|--------------------------------|
| Description: | Type A7068, self-adhesive |
| Colour: | brown (natural) + yellow liner |

| Testing | Test value | Unit | Test standard |
|--|-------------|------------------|---------------|
| Nominal Thickness, coated glass fabric | 0,138 | mm | |
| Coating | 65 | % | |
| Total PTFE coated fabric weight | 296 | g/m ² | ISO 2286-2 |
| Adhesive Type | Silicone | | |
| Athesive Thickness | 0,060 | mm | ISO 2286-3 |
| Total Product Thickness | 0,198 | mm | |
| Adhesive Strength typical / minimum | 12 / 10 | N/25,4mm | ISO 8510-2 |
| Operating Temperature | -73 to +260 | °C | - |

| Main features | This type is a PTFE-coated fabric with a high performance, silicone pressure-sensitive adhesive on one side. The PTFE surface exhibits good release properties in demanding high temperature applications. The product has a yellow corrugated liner to protect the adhesive surface and to ease identification and use. |
|------------------------|---|
| Preferred fields | This type is particularly recommended for PVC-U welding. |
| Conditions of storage: | Recommondation: Indoors in clean rooms at room temperature; ≈ 20°C / ≈ 50% rel. humidity. Storage away from direct sunlight. Avoid direct contact with liquid water before application of the tape. |
| Shelf life: | - Min. shelf life of 18 months after production date. |
| Conformities: | EC 1907/2006 (REACH) incl. EU 2021/1297. EU guidelines:2011/65/EC (RoHS); 2015/863/EC (RoHS 3) EU Regulation EC 2019/1021 Persistent Organic Pollutants (POPs) EU Regulation EC 2018/851,94/62 and 2004/14/EC. |

This information is based on our available data. These values are within the normal tolerance range of material properties and do not represent guaranteed property values. Therefore they shall not be used for specification purposes. The customer is solely responsible for quality and suitability of material for his application. He has to test usage and processing prior to use. Angst+Pfister makes no guarantees for the suitability of the material for any given application and assumes no obligation or liability in connection with the information provided above.

www.angst-pfister.com

Erstelldatum/Visum: 24.01.2025/RIC

Geprüft/Visum: 27.01.2025/RIC Freigegeben/Visum: 27.01.2025/RIC